

Purolite® A848

Polyacrylic Gel Weak Base Anion
Resin Free Base form

PRINCIPAL APPLICATIONS

- Demineralization - High organics water

ADVANTAGES

- Lower rinse volumes
- Excellent resistance to organic fouling

SYSTEMS

- Coflow regenerated systems
- Counterflow regenerated systems

TYPICAL PACKAGING

- 1 ft³ Sack
- 25 L Sack
- 5 ft³ Drum (Fiber)
- 1 m³ Supersack
- 42 ft³ Supersack

TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Polymer Structure	Gel polyacrylic crosslinked with divinylbenzene
Appearance	Spherical Beads
Ionic Form	FB form
Total Capacity (min.)	1.4 eq/L (30.6 Kgr/ft ³) (FB form)
Moisture Retention	59 - 65 % (FB form)
Particle Size Range	300 - 1200 µm
< 300 µm (max.)	1 %
Uniformity Coefficient (max.)	1.7
Reversible Swelling, FB → Cl ⁻ (max.)	15 %
Specific Gravity	1.07
Shipping Weight (approx.)	675 - 705 g/L (42.2 - 44.1 lb/ft ³)
Temperature Limit	40 °C (104.0 °F) (FB form)



Americas
T +1 610 668 9090
F +1 610 668 8139
americas@purolite.com

Europe
T +44 1443 229334
F +44 1443 227073
europe@purolite.com

Asia Pacific
T +86 571 876 31382
F +86 571 876 31385
asiapacific@purolite.com