PRODUCT DATA SHEET

Purolite™ C115HMR

Polymethacrylic Powder
Polymethacrylic Acid Forme hydrogène

APPLICATIONS PRINCIPALES

- Résine Polacrilex

AVANTAGES

- Excellent chemical and physical stability
- Secure, validated supply and regulatory support

AUTORISATIONS RÉGLEMENTAIRES

- Kosher
- Fabriqué dans des conditions cGMP
- TSE/BSE/GMO free
- Pharmacopeia compliant

CONDITIONNEMENT CLASSIQUE

- Petit fût (fibre)

CARACTÉRISTIQUES PHYSICO-CHIMIQUES TYPIQUES

Structure polymérique	Polymethacrylic crosslinked with divinylbenzene
Apparence	Off-white powder
Groupe fonctionnel	Carboxylic acid
Forme ionique	H^+ form
Capacité massique sèche (min.)	10 eq/kg (Forme hydrogène)
Taux d'humidité (max.)	5 %
Plage de granulométrie des billes	<150 µm
Impurities Iron (max.)	10 ppm
Impurities Heavy Metals as Pb (max.)	10 ppm
Teneur en arsenique (max.)	3 ppm
Taux de sodium (poids sec)	0.2 %

2026 Purolite
All rights reserved.

Ecolab is a global developer, manufacturer, and supplier of Purolite™ Resins including ion exchange, catalyst adsorbent and advanced polymers that make the world cleaner and healthier.

www.puroliteresins.com

We're ready to solve your process challenges.

For further information on products and services, visit www.puroliteresins.com or complete a Contact Us form via PuroliteResins.com/contact-us or use the QR code.

Contact Us Form:

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Purolite expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

2026 Purolite
All rights reserved.