

Chromalite® MDEA/M

**Diethylamino Methacrylate
Macroporosa Weak Anion
Exchanger**

The Chromalite M range of chromatographic resins are hydrophilic, macroporous, methacrylic resins for large-scale applications. Based on a rigid polymeric backbone that ensures excellent pressure-flow properties, they have been designed for high performance, stability and reliability under the conditions of modern industrial bioprocesses.

Chromalite M resins for ion exchange chromatography include both strong and weak functional groups in both anion and cation exchange processes.

Chromalite MDEA/M is a weak anion exchanger with optimal porosity and high mechanical stability.

PRINCIPALI APPLICAZIONI

- Cromatografia a scambio ionico
- Protein purification (up to 250 kDa)
- Purification of peptides obtained by fermentation
- Preparative chromatography

VANTAGGI

- Hydrophilic
- High mechanical stability

CERTIFICAZIONI

- esente da TSE BSE OGM
- Risoluzione del Consiglio d'Europa ResAP (2004)3
- Halal
- Kosher

IMBALLI TIPICI

- 25ml
- 100ml
- 500ml
- 1L
- 5L
- 10L

* Shipped in wet form

CARATTERISTICHE CHIMICHE E FISICHE TIPICHE:

Distribuzione granulometrica - μm	75 - 125
Gruppo funzionale	Diethylamino Methacrylate
Diametro dei pori	1000 Å
Pressione di lavoro (max.)	20 bar
Capacità totale (min.)	20 mg/ml
Condizioni ottimali di conservazione	2 - 20 °C
Fornito come	Wet

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Purolite expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.