SCHEDA TECNICA

Purolite™ Puromet™ MTA5601

Polistirenica Macroporosa, Resina anionica forte, Forma cloruro, Grado Resin In Pulp

PRINCIPALI APPLICAZIONI

- Estrazione dell'uranio

VANTAGGI

- Eccezionale stabilità fisica
- Alta captazione dell'Uranio
- Perle di grandi dimensioni

SISTEMI

- Soluzioni acide e polpe
- Processi con Resin-In-Pulp (RIP)

IMBALLI TIPICI

- Sacco da 1 CF
- Sacco da 25 litri
- Fusto da 5 CF (in fibra)
- Saccone da 1 m3
- Saccone da 42 CF

CARATTERISTICHE CHIMICHE E FISICHE TIPICHE:

Struttura del Polimero	Polistirene macroporoso reticolato con divinilbenzene
Aspetto	Perle sferiche
Gruppo Funzionale	Pyridinium
Forma Ionica	forma Cl^-
Capacità totale (min.)	1.2 eq/L (26.2 Kgr/ft³) (forma Cl^-)
Umidità	49 - 56 % (forma Cl^-)
Distribuzione granulometrica	800 - 1300 µm
< 800 µm (max.)	5 %
Peso di spedizione (approx.)	680 - 740 g/L (42.5 - 46.2 lb/ft³)

2026 Purolite
All rights reserved.

Ecolab is a global developer, manufacturer, and supplier of Purolite™ Resins including ion exchange, catalyst adsorbent and advanced polymers that make the world cleaner and healthier.

www.puroliteresins.com



We're ready to solve your process challenges.

For further information on products and services, visit www.puroliteresins.com or complete a Contact Us form via PuroliteResins.com/contact-us or use the QR code.

Contact Us Form:

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Purolite expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

2026 Purolite
All rights reserved.