PRODUCT DATA SHEET

Purolite™ MB400Black

Polystyrenic Gel, Gel, Mixed Bed Resin, Hydrogen form, Hydroxide form, Darker color cation component

PRINCIPAL APPLICATIONS

- Demineralization - Mixed Bed
- Cartridges

ADVANTAGES

- General purpose

SYSTEMS

- Mixed Bed
- Cartridges

REGULATORY APPROVALS

- IFANCA Halal Certified

TYPICAL PACKAGING

- 1 ft³ Sack
- 25 L Sack
- 5 ft³ Drum (Fiber)

TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Appearance	Spherical Beads	
Moisture Content (max.)	65 %	
Particle Size Range	300 - 1200 µm	
< 300 µm (max.)	1 %	
Uniformity Coefficient (max.)	1.7	
Shipping Weight (approx.)	705 - 740 g/L (44.1 - 46.2 lb/ft³)	
Temperature Limit, Non-Regenerable Bed	100 °C (212.0 °F)	
Temperature Limit, Regenerable Bed	60 °C (140.0 °F)	
Component Name	Gel Strong Acid Cation	Gel Type I Strong Base Anion
Polymer Structure	Gel polystyrene crosslinked with divinylbenzene	Gel polystyrene crosslinked with divinylbenzene
Functional Group	Sulfonic Acid	Type I Quaternary Ammonium
Ionic Form	H^+ form	OH^- form
Cation / Anion Volumetric Ratio	40 %	60 %

2026 Purolite
All rights reserved.

Ecolab is a global developer, manufacturer, and supplier of Purolite™ Resins including ion exchange, catalyst adsorbent and advanced polymers that make the world cleaner and healthier.

www.puroliteresins.com

We're ready to solve your process challenges.

For further information on products and services, visit www.puroliteresins.com or complete a Contact Us form via PuroliteResins.com/contact-us or use the QR code.

Contact Us Form:

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Purolite expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

2026 Purolite
All rights reserved.