

# Purolite™ WCA100

Polystyrenic Gel, Amphoteric Resin,  
Self-neutralized internal salt,  
Chromatographic Grade

## PRINCIPAL APPLICATIONS

- Separation of salts from solutions by ion retardation

## ADVANTAGES

- Controlled particle size
- Balanced cation and anion functionality

## TYPICAL PACKAGING

- 1 ft<sup>3</sup> Sack
- 25 L Sack
- 5 ft<sup>3</sup> Drum (Fiber)
- 1 m<sup>3</sup> Supersack
- 42 ft<sup>3</sup> Supersack

## TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Polymer Structure	Gel polystyrene crosslinked with divinylbenzene
Appearance	Spherical Beads
Functional Group	Carboxylic acid / Quaternary ammonium
Ionic Form	Self-neutralized internal salt
Total Capacity (min.)	0.8 eq/L
Moisture Content	48 - 57 %
Particle Size (85% in the range)	260 ± 20 µm
< 210 µm (max.)	1 %
Specific Gravity	1.1
Shipping Weight (approx.)	700 - 780 g/L (43.8 - 48.8 lb/ft <sup>3</sup> )
Temperature Limit	60 °C (140.0 °F)

Ecolab is a global developer, manufacturer, and supplier of Purolite™ Resins including ion exchange, catalyst adsorbent and advanced polymers that make the world cleaner and healthier.

[www.puoliteresins.com](http://www.puoliteresins.com)



## We're ready to solve your process challenges.

For further information on products and services, visit [www.puoliteresins.com](http://www.puoliteresins.com) or complete a Contact Us form via [PuoliteResins.com/contact-us](http://PuoliteResins.com/contact-us) or use the QR code.

Contact Us Form:



The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Purolite expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

