

Praesto® Jetted SP35

Highly Cross Linked Strong
Cation Exchanger uniform
agarose particle beads

Praesto Jetted SP35 is an agarose-based, strong acid cation exchange resin designed for biomolecule purification, including proteins, peptides and oligonucleotides. It is manufactured using 'Jettling' - a new, patented method that produces agarose beads with a very narrow particle size distribution.

Purolite is the first agarose resin provider to produce process-scale volumes of uniform particle size beads.

[Praesto Ion Exchange Chromatography Resins - FAQs](#)

GÓWNE ZASTOSOWANIA

- MAb Purification
- Protein purification (20-500 kDa)

ZALETY

- Uniform particle size
- Enhanced productivity
- High dynamic binding capacity
- Enhanced pressure/flow performance
- Manufactured with reduced environmental impact
- Secure, validated supply and regulatory support

ZGODNO Z REGULACJAMI

- Manufactured under cGMP conditions

DOSTPNO OPAKOWA

- Bulk Resin
- Production-Scale OPUS® Columns
- OPUS® Robocolumns®
- OPUS® MiniChrom Columns
- HT Columns

PODSTAWOWE WACIWOŚCI FIZYCZNE I CHEMICZNE:

Matrix	Cross-linked agarose
grupa funkcyjna	CH ₂ CH ₂ CH ₂ S03
Ionic Capacity, mmol/mL Resin	0.11-0.16
Average Particle Size (d ₅₀), μm	35
Flow Velocity cm/h at 3 bar in a 2.6 x 20 cm Column (packed at 4 bar)	> 150
Binding Capacity mg/mL Resin at 6' Residence Time	> 90 mg/ml IgG
Operating pH Stability (Short Term)	pH 3-14
Operating pH Stability (Long-Term)	pH 4-13
Working Temperature	4-30°C
Chemical stability	All commonly used aqueous buffers, 1M NaOH, 8M urea, 6M guanidine hydrochloride, 30% isopropanol and 70% ethanol
Avoid	Oxidizing agents, cationic detergents




Americas
T +1 610 668 9090
F +1 610 668 8139
americas@purolite.com

**EMEA(Europa, Środkowy
Wschód i Afryka)**
T +44 1443 229334
F +44 1443 227073
europe@purolite.com


Asia Pacific
T +86 571 876 31382
F +86 571 876 31385
asiapacific@purolite.com

FSU
T +7 495 363 5056
F +7 495 564 8121
fsu@purolite.com

Praesto® Jetted Beads



Standard Agarose Beads



The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Purolite expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.