

# Purolite™ Shallow Shell™ SSTPPC80

polistyrenowy żelowy, żywica  
kationitowa silnie kwaśna, forma  
sodowa, Shallow Shell™ Technology,  
uziarnienie dla systemu Puropack

## GŁÓWNE ZASTOSOWANIA

- zmiękczenie - przemysł

## ZALETY

- SST shorter diffusion path benefits:
- wysoka skuteczność regeneracji
- Very low leakage
- Highly resistant to iron fouling
- małe objętości wody płucznej
- Lower operating costs
- doskonała stabilność fizyko-chemiczna

\* SST jest znakiem handlowym firmy Purolite

## SYSTEMY

- systemy złożów upakowanych

## DOSTĘPNOŚĆ OPAKOWAŃ

- worek 1 ft<sup>3</sup>
- worek 6 ft<sup>3</sup>
- beczka 6 ft<sup>3</sup>

## PODSTAWOWE WŁAŚCIWOŚCI FIZYCZNE I CHEMICZNE:

Struktura polimeru	żelowy polistyren sieciowany dwuwinylobenzenem
Wygląd	kuliste ziarna
Grupy funkcyjne	kwasy sulfonowe
Forma jonowa	forma Na <sup>+</sup>
pojemność w suchej masie (min.)	4.0 val/kg (forma Na <sup>+</sup> )
zawartość wilgoci	42 - 48 % (forma Na <sup>+</sup> )
główna średnica	650 ± 50 μm
współczynnik jednorodności (max.)	1.25
Pęcznienie odwracalne, Na <sup>+</sup> → H <sup>+</sup> (max.)	6 %
ciężar właściwy	1.2
ciężar nasypowy (średnio)	775 - 825 g/L (48.4 - 51.6 lb/ft <sup>3</sup> )
limit temperatury	100 °C (212.0 °F)

Ecolab is a global developer, manufacturer, and supplier of Purolite™ Resins including ion exchange, catalyst adsorbent and advanced polymers that make the world cleaner and healthier.

[www.puroliteresins.com](http://www.puroliteresins.com)



We're ready to solve your process challenges.

For further information on products and services, visit [www.puroliteresins.com](http://www.puroliteresins.com) or complete a Contact Us form via [PuroliteResins.com/contact-us](http://PuroliteResins.com/contact-us) or use the QR code.

Contact Us Form:



The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Purolite expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.