

# Purolite® A848

Polyacrylic Gel, Weak Base Anion  
Resin, Free Base form

## PRINCIPAL APPLICATIONS

- Demineralization - High organics water

## ADVANTAGES

- Lower rinse volumes
- Excellent resistance to organic fouling

## SYSTEMS

- Coflow regenerated systems
- Counterflow regenerated systems

## TYPICAL PACKAGING

- 1 ft<sup>3</sup> Sack
- 25 L Sack
- 5 ft<sup>3</sup> Drum (Fiber)
- 1 m<sup>3</sup> Supersack
- 42 ft<sup>3</sup> Supersack

## TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Polymer Structure	Gel polyacrylic crosslinked with divinylbenzene
Appearance	Spherical Beads
Ionic Form	FB form
Total Capacity (min.)	1.4 eq/L (30.6 Kgr/ft <sup>3</sup> ) (FB form)
Moisture Retention	59 - 65 % (FB form)
Particle Size Range	300 - 1200 µm
< 300 µm (max.)	1 %
Uniformity Coefficient (max.)	1.7
Reversible Swelling, FB → Cl <sup>-</sup> (max.)	15 %
Specific Gravity	1.07
Shipping Weight (approx.)	675 - 705 g/L (42.2 - 44.1 lb/ft <sup>3</sup> )
Temperature Limit	40 °C (104.0 °F) (FB form)



**Americas**  
T +1 610 668 9090  
F +1 610 668 8139  
americas@purolite.com

**Europe**  
T +44 1443 229334  
F +44 1443 227073  
europe@purolite.com

**Asia Pacific**  
T +86 571 876 31382  
F +86 571 876 31385  
asiapacific@purolite.com