

Purolite® CT122

Polystyrenic Gel, Strong Acid Cation
Resin, Hydrogen form, Catalyst

PRINCIPAL APPLICATIONS

- Bisphenol-A synthesis

TYPICAL PACKAGING

- 1 m³ Supersack
- 42 ft³ Supersack

TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Polymer Structure	Gel polystyrene crosslinked with divinylbenzene
Appearance	Spherical Beads
Functional Group	Sulfonic Acid
Ionic Form	H ⁺ form
Dry Weight Capacity (min.)	5 eq/kg (H ⁺ form)
Moisture Retention	78 - 82 % (H ⁺ form)
< 350 µm (max.)	1 %
< 425 µm (max.)	2 %
< 850 µm (max.)	5 %
> 1180 µm (max.)	2 %
Shipping Weight (approx.)	700 - 730 g/L (43.8 - 45.6 lb/ft ³)
Temperature Limit	130 °C (266.0 °F)



Americas
T +1 610 668 9090
F +1 610 668 8139
americas@purolite.com

EMEA
T +44 1443 229334
F +44 1443 227073
europe@purolite.com

Asia Pacific
T +86 571 876 31382
F +86 571 876 31385
asiapacific@purolite.com