

Purofine® PFA503OH

Polystyrenic Macroporous, Type I
Strong Base Anion Resin, Hydroxide
form, Uniform Particle Size

PRINCIPAL APPLICATIONS

- Demineralization

ADVANTAGES

- High operating capacity

TYPICAL PACKAGING

- 1 CF Box
- 5 ft³ Drum (Fiber)

TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Polymer Structure	Macroporous polystyrene crosslinked with divinylbenzene
Appearance	Spherical Beads
Functional Group	Type I Quaternary Ammonium
Ionic Form	Cl ⁻ form
Total Capacity	1 eq/L (21.8 Kgr/ft ³) (Cl ⁻ form)
Mean Diameter	605 ± 55 µm
Uniformity Coefficient	1.1 - 1.2
Moisture Retention	61 - 66 % (Cl ⁻ form)
Specific Gravity	1.07
Shipping Weight (approx.)	650 - 690 g/L (40.6 - 43.1 lb/ft ³)
Reversible Swelling, Cl ⁻ → OH ⁻ (max.)	20 %
Temperature Limit	100 °C (212.0 °F) (Cl ⁻ form)
Temperature Limit	60 °C (140.0 °F) (OH ⁻ form)



Americas
T +1 610 668 9090
F +1 610 668 8139
americas@purolite.com

EMEA
T +44 1443 229334
F +44 1443 227073
europe@purolite.com

Asia Pacific
T +86 571 876 31382
F +86 571 876 31385
asiapacific@purolite.com