

Purosorb™ PAD610

Polymethacrylic/DVB Macroporoso,
Resina Adsorvente, Forma Não-
Iônica

APLICAÇÕES PRINCIPAIS

- Recuperação de Anticorpos
- Recuperação da enzima
- Recuperação de proteínas
- Remoção de amargor de suco
- Extração de vitamina B e E
- Extração de polifenol

VANTAGENS

- Regeneração eficiente
- Alta Porosidade

APROVAÇÕES REGULAMENTARES

- OK Kosher Certified
- Certificado Halal LPPOM MUI
- Certificado IFANCA Halal
- Em conformidade com a Resolução Européia ResAP 2004 3
- Livre de GMO/TSE/BSE

EMBALAGEM TÍPICA

- Saco de 1 pé³
- Saco de 25 Litros
- Tambor (Fibra) de 5 pé³
- BIGBAG de 1m³
- BIGBAG de pé³
- Tambor (Plástico) de 50 Litros

CARACTERÍSTICAS FÍSICO-QUÍMICAS TÍPICAS:

Estrutura Polimérica	Reticulado de polimetacrílico com divinilbenzeno
Aparência	White to off-white spherical beads
Grupo Funcional	não iônico
Forma Iônica	Nenhum
Retenção de Umidade	60 - 66 %
Faixa de Tamanho de esferas	350 - 1200 µm
Typical Pore Diameter by nitrogen adsorption	300 Å
Typical Pore Volume by nitrogen adsorption	1.2 mL/g
Typical Surface Area by nitrogen adsorption	490 m ² /g
Peso Específico	1.1
Peso de Embarque (aprox.)	650 - 710 g/L (40.6 - 44.4 lb/ft ³)
Limite de pH, Estabilidade	0 - 14
Limite de Temperatura	100 °C (212.0 °F)



Algeria
Australia
Bahrain
Brazil
Canada
China
Czech Republic
France
Germany

India
Indonesia
Israel
Italy
Japan
Jordan
Kazakhstan
Korea
Malaysia

Mexico
Morocco
New Zealand
Poland
Romania
Russia
Singapore
Slovak Republic
South Africa

Spain
Taiwan
Tunisia
Turkey
UK
Ukraine
USA
Uzbekistan



Americas

Purolite Corporation
2201 Renaissance Blvd.
King of Prussia, PA 19406
T +1 800 343 1500
T +1 610 668 9090
F +1 800 260 1065
americas@purolite.com

EMEA

Purolite Ltd.
Unit D
Llantrisant Business Park
Llantrisant, Wales, UK
CF72 8LF
T +44 1443 229334
F +44 1443 227073
emea@purolite.com

FSU

Purolite Ltd.
Office 6-1
36 Lyusinovskaya Str.
Moscow, Russia
115093
T +7 495 363 5056
F +7 495 564 8121
fsu@purolite.com

Asia Pacific

Purolite China Co. Ltd.
Room 707, C Section
Huanglong Century Plaza
No.3 Hangda Road
Hangzhou, Zhejiang, China 310007
T +86 571 876 31382
F +86 571 876 31385
asiapacific@purolite.com

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Purolite expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

