FICHA TÉCNICA

Purolite™ C115HMR

Polymethacrylic Powder
Polymethacrylic Acid Forma de hidrogénio

APLICAÇÕES PRINCIPAIS

- Resina Polacrilex

VANTAGENS

- Excelente estabilidade química e física
- Fornecimento e suporte regulatório seguro e validado

APROVAÇÕES REGULAMENTARES

- Kosher
- Fabricado sob condições cGMP
- Livre de TSE BSE GMO
- Compatível com a Farmacopéia

EMBALAGEM TÍPICA

- Pequeno tambor de fibra

CARACTERÍSTICAS FISICO-QUÍMICAS TÍPICAS:

Estrutura Polimérica	Polymethacrylic crosslinked with divinylbenzene
Aparência	Off-white powder
Grupo funcional	Carboxylic acid
Forma iônica	H^+ form
Capacidade em Peso Seco (min.)	10 eq/kg (Forma de hidrogénio)
Teor de umidade (máx.)	5 %
Faixa de Tamanho de Esferas	<150 µm
Impurities Iron (max.)	10 ppm
Impurities Heavy Metals as Pb (max.)	10 ppm
Teor de arsênico (máx.)	3 ppm
Teor de sódio (peso seco)	0.2 %

2026 Purolite
All rights reserved.

Ecolab is a global developer, manufacturer, and supplier of Purolite™ Resins including ion exchange, catalyst adsorbent and advanced polymers that make the world cleaner and healthier.

www.puroliteresins.com

We're ready to solve your process challenges.

For further information on products and services, visit www.puroliteresins.com or complete a Contact Us form via PuroliteResins.com/contact-us or use the QR code.

Contact Us Form:

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Purolite expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

2026 Purolite
All rights reserved.