

Purolite™ Purofine™ PFA500MBOHPlus

polistiren macroporos, Rasinina Anionica puternic bazica de tip I, Forma hidroxid, Dimensiunea uniformă a particulelor, Categoria pat mixt

PRINCIPALELE APLICATII

- demineralizare
- Component anionic pentru pat mixt

AVANTAJE

- Tratat antistatic, pentru o separare mai ușoară de componentul cationic al patului mixt
- eficiență ridicată de regenerare
- Dimensiunea uniformă a particulelor
- rezistență bună la otrăvire cu compusi organici
- rezistență sporită la oc termic i osmotic

SISTEME

- Paturi mixte regenerabile
- Working Mixed Bed
- Polishing Mixed Bed

AMBALAJE TIPICE

- sac 1 ft³
- 25 L sac
- Butoi (Fibră) de 5 CF
- 1 M³ supersac
- supersac de 42 CF

CARACTERISTICI TIPICE FIZICE SI CHIMICE

Structura polimerica	polimer polistiren macroporos reticulat cu DVB
Aspect	Perle sferice
Grupari functionale	Grupari quaternare de amoniu tip I
Forma ionica	forma OH ⁻
Capacitatea totală (min.)	1.1 eq/L (24.0 Kgr/ft ³) (forma Cl ⁻)
reineria umidității	54 - 65 % (forma Cl ⁻)
diametru mediu	605 ± 55 μm
coeficient de uniformitate	1.1 - 1.2
Dilatare reversibilă, Cl ⁻ → OH ⁻ (max.)	20 %
densitate specifică	1.07
Greutate de transport (aprox.)	650 - 700 g/L (40.6 - 43.8 lb/ft ³)
Limita de temperatură	100 °C (212.0 °F) (forma Cl ⁻)
Limita de temperatură	65 °C (149.0 °F) (forma OH ⁻)

Ecolab is a global developer, manufacturer, and supplier of Purolite™ Resins including ion exchange, catalyst adsorbent and advanced polymers that make the world cleaner and healthier.




www.puoliteresins.com



We're ready to solve your process challenges.

For further information on products and services, visit www.puoliteresins.com or complete a Contact Us form via PuoliteResins.com/contact-us or use the QR code.

Contact Us Form:



The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Purolite expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

