PRODUCT DATA SHEET

Purolite™ Select SRA5500OH

polistirenic Gel, Rasinina Anionica puternic bazica de tip I, Forma hidroxid, Dimensiunea uniformă a particulelor, Premium Grade

PRINCIPALELE APLICATII

- demineralizare - apă de puritate mare

AVANTAJE

- Capacitate ridicată de operare
- Rezistenă excelentă la ocul osmotic
- Dimensiunea uniformă a particulelor
- Tratat antistatic, pentru o separare mai uoară de componentul cationic al patului mixt

SISTEME

- Paturi mixte folosite la purificarea condensului
- Makeup Polishing Mixed Bed
- RO Polishing Mixed Bed
- Working Mixed Bed

AMBALAJE TIPICE

- sac 1 ft³
- 25 L sac
- Butoi (Fibră) de 5 CF
- 1 M³ supersac
- supersac de 42 CF

CARACTERISTICI TIPICE FIZICE SI CHIMICE

Structura polimerica	Copolimer gel polistirenic reticulat cu divinilbenzen
Aspect	Perle sferice
Grupari functionale	Grupari quaternare de amoniu tip I
Forma ionica	OH-
Capacitatea totală (min.)	1.1 eq/L (24.0 Kgr/ft³) (forma OH^-)
reinerea umidităii	54 - 63 % (forma OH^-)
diametru mediu	590 ± 50 µm
coeficient de uniformitate (max.)	1.2
< 300 µm (max.)	0.5 %
< 850 µm (max.)	99 %
granule întregi (max.)	99 %
conversie (min.)	90 % (forma OH^-)
Valoarea medie a rezistentei la spargere	350 g
Breaking Weight <200 g (max.)	5 %
Dilatare reversibilă, Cl- → OH- (max.)	24 %
densitate specifică	1.08
Greutate de transport (aprox.)	660 - 700 g/L (41.2 - 43.8 lb/ft³)
fier rezidual (max.)	100 ppm
plumb rezidual (max.)	50 ppm
Residual Aluminum (max.)	50 ppm
Residual Copper (max.)	50 ppm
Limita de temperatură	100 °C (212.0 °F) (forma Cl^-)

2026 Purolite
All rights reserved.

Limita de temperatură	60 °C (140.0 °F) (forma OH^-)
Recommended Mixed Bed Pairing	Purolite™ Select SRC6500H, SRC6500Na


2026 Purolite
All rights reserved.

Caracteristici hidraulice

PRESSURE DROP

The pressure drop across a bed of ion exchange resin depends on the particle size distribution, bed depth, and voids volume of the exchange material, as well as on the flow rate and viscosity of the influent solution. Factors affecting any of these parameters—such as the presence of particulate matter filtered out by the bed, abnormal compressibility of the resin, or the incomplete classification of the bed—will have an adverse effect, and result in an increased head loss. Depending on the quality of the influent water, the application and the design of the plant, service flow rates may vary from 10 to 40 BV/h.

PRESSURE DROP ACROSS RESIN BED



Ecolab is a global developer, manufacturer, and supplier of Purolite™ Resins including ion exchange, catalyst adsorbent and advanced polymers that make the world cleaner and healthier.

www.puroliteresins.com



We're ready to solve your process challenges.

For further information on products and services, visit www.puroliteresins.com or complete a Contact Us form via PuroliteResins.com/contact-us or use the QR code.

Contact Us Form:

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Purolite expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

2026 Purolite
All rights reserved.