

Purolite™ Shallow Shell™ SSTPFA63

polistirenic Gel, Răină Anionică puternic bazica de tip II, forma clor,

Technologia Shallow Shell™, Dimensiunea uniformă a particulelor

PRINCIPALELE APLICATII

- demineralizare
- Îndepărtarea silicei

AVANTAJE

- SST shorter diffusion path benefits:
- Cea mai mare eficiență de regenerare
- Very low leakage
- Volumuri scăzute de clătire
- Lower operating costs
- stabilitate fizică i chimică excelentă

SISTEME

- sisteme de regenerare in co-curent
- sisteme de regenerare in contracurent

APROBARI DE REGLEMENTARE

- Certificat de WQA conform standardului NSF ANSI 61

AMBALAJE TIPICE

- sac 1 ft³
- 25 L sac
- Butoi (Fibră) de 5 CF
- 1 M³ supersac
- supersac de 42 CF

* SST® este marca inregistrata a Purolite Co.

CARACTERISTICI TIPICE FIZICE SI CHIMICE

Structura polimerica	Copolimer gel polistirenic reticulat cu divinilbenzen
Aspect	Perle sferice
Grupari functionale	Grupari quaternare de amoniu de tip II
Forma ionica	forma Cl ⁻
capacitate masica uscată (min.)	2.6 eq/kg uscat (forma Cl ⁻)
reinerea umidității	37 - 45 % (forma Cl ⁻)
diametru mediu	570 ± 50 μm
coeficient de uniformitate (max.)	1.1 - 1.2
Dilatare reversibilă, Cl ⁻ → OH ⁻ (max.)	15 %
densitate specifică	1.12
Greutate de transport (aprox.)	670 - 710 g/L (41.9 - 44.4 lb/ft³)
Limita de temperatură	35 °C (95.0 °F)

Ecolab is a global developer, manufacturer, and supplier of Purolite™ Resins including ion exchange, catalyst adsorbent and advanced polymers that make the world cleaner and healthier.

www.puroliteresins.com



We're ready to solve your process challenges.

For further information on products and services, visit www.puroliteresins.com or complete a Contact Us form via PuroliteResins.com/contact-us or use the QR code.

Contact Us Form:



The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Purolite expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.