

Purolite® MB35

聚苯乙烯 大孔, 大孔, 混床树脂, 氢型,
氢氧型

主要应用

- 脱盐 - 混床
- 凝结水精处理

产品优势

- 高工作交换容量
- 顺流再生系统
- 逆流再生系统
- 非再生型

适用系统

- 混床

包装样式

- 1 CF 编织袋
- 25L 阀口袋
- 5 CF 纤维板桶

典型物理和化学参数

外观	球状颗粒	
含水量 (最大)	65 %	
粒径分布	300 - 1200 µm	
< 300 µm (最大)	1 %	
均一系数 (最大)	1.7	
包装密度 (大约)	715 - 750 g/L (44.7 - 46.9 lb/ft³)	
温度限制, 不可再生床	100 °C (212.0 °F)	
温度限制, 可再生床	60 °C (140.0 °F)	
组分名称	大孔强酸阳树脂	凝胶I型强碱阴树脂
聚合物骨架	大孔型聚苯乙烯二乙烯苯交联	凝胶型聚苯乙烯二乙烯苯交联
官能团	磺酸	季铵I型
离子形态	H ⁺	OH ⁻
阳离子/阴离子体积比	35 %	65 %



Algeria
Australia
Bahrain
Brazil
Canada
China
Czech Republic
France
Germany

India
Indonesia
Israel
Italy
Japan
Jordan
Kazakhstan
Korea
Malaysia

Mexico
Morocco
New Zealand
Poland
Romania
Russia
Singapore
Slovak Republic
South Africa

Spain
Taiwan
Tunisia
Turkey
UK
Ukraine
USA
Uzbekistan



Americas

Puro-lite
2201 Renaissance Blvd.
King of Prussia, PA 19406
T +1 800 343 1500
T +1 610 668 9090
F +1 800 260 1065
americas@puro-lite.com

EMEA

Puro-lite Ltd.
Unit D
Llantrisant Business Park
Llantrisant, Wales, UK
CF72 8LF
T +44 1443 229334
F +44 1443 227073
emea@puro-lite.com

FSU

Puro-lite Ltd.
Office 6-1
36 Lyusinovskaya Str.
Moscow, Russia
115093
T +7 495 363 5056
F +7 495 564 8121
fsu@puro-lite.com

Asia Pacific

Puro-lite China Co. Ltd.
Room 707, C Section
Huanglong Century Plaza
No.3 Hangda Road
Hangzhou, Zhejiang, China 310007
T +86 571 876 31382
F +86 571 876 31385
asiapacific@puro-lite.com

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Puro-lite expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

